

Technical Information

Width/	Fabric	Fiber Content	Weight	Protective	Abrasion	Light-	Approx.	CI.
Pattern	Grade	& Backing		Finish	Resistance	fastness	Repeats	Code
60" Oasis	1	100% Polyester	350g/y±5%	N/A	100,000 Double Rubs	4	N/A	WS

EXPLANATION OF ACT ICONS FOR UPHOLSTERY



Flammability testing determined as fabric's resistance to burning.

PASSES California 117

Colorfastness to Wet and Dry Crocking

Colorfastness to wet & dry crocking refers to the rubbing off of color from the fabric onto clothing, hands or other materials and can occur under wet or dry conditions.

PASSES Class 5 Dry, Class 4.5 Wet

Colorfastness to Light

Colorfastness to light is the degree to which fabric will retain its color when exposed to light.

PASSES Class 4 minimum at 40 hours. NOTE: Class 4 minimum at 60 hours is recommended for direct sunlight exposure situations.

Abrasion

Abrasion is the ability of a fabric to withstand damage from wear and rubbing. There is a general contract specification as well as heavy duty specification.

A (General Contract) 100,000 double rubs

Cleaning Code Definitions

WS Clean with water-based cleaning agents, foam or pure, water-free solvents (Energine, Carbona, Renuzit or other similar products). Vacuuming or light brushing is recommended to prevent dust and soil buildup.

QUICKSHIP